

IN THE ABSTRACT

Page 34, please amend the abstract as follows:

Abstract

A power transmission belt, and more particularly a toothed power transmission belt, comprising a longitudinally extending tensile member composed of one or more carbon fiber cords, wherein ~~the belt exhibits belt growth of not more than 0.1% based on its original length after 48 hours under High Temperature Belt Growth Analysis performed at 100°C, and a method for producing such belts exhibiting reduced belt growth.~~ the cords are treated with an elastomer latex coating, and that the cord treatment composition further comprises a resorcinol-formaldehyde reaction product, and that such cord treatment composition possesses an elastic modulus at a temperature of 20°C to be within the range of from about 1.0×10^7 dynes/cm² to about 5.0×10^8 dynes/cm², and at a temperature of 100°C to be within the range of from about 5.0×10^6 dynes/cm² to about 4.0×10^8 dynes/cm².